



ACRO Sales & Engineering, Inc.

N57 W13366 Carmen Avenue • Menomonee Falls, WI 53051-6101 • Phone: (262) 781-8940
Fax: (262) 781-8964 • Toll Free: (877) SOLDERS • E-Mail: sales@acrosales.com • Website: www.acrosales.com

580HT Acroloy Bar Solder

General characteristics:

Alloy: SN5/PB94/AG1
High Temperature, (HMP) Bar Solder

Chemical Characteristics:

Amount of Tin (Sn)	: 5% ± 0.5%
Amount of Lead (Pb)	: 94% ± 0.5%
Amount of Silver (Ag)	: .8 % - 1.2%

Maximum impurities:

Cu	Cd	Sb	Bi	Fe	Zn	Al	As	Others
0.05%	0.002%	0.05%	0.01%	0.02%	0.001%	0.001%	0.001%	0.05%

Physical Characteristics:

Alloy: SN5/PB94/AG1
Melting Point : Solidus @ 296°C to liquidus @ 302°C
Specific Weight : 11.04 g/cm³
Working temperature : 350 – 460 °C

Packaging:

Packed in cartons of : 50 Pounds (Smaller quantities available in needed)
Identification : Boxes carry product information. Bars stamped 580HT.
Quality assurance : A certificate of conformity can be issued for each
shipment if requested at the time of ordering.
Storage : at room temperature is unlimited.